

Property	Test Condition	Test Method ISO	Units	High gloss
				Middle impact
				700 SG5
				>ABS<
<b>Physical property</b>				
Density	23°C	ISO1183	kg/m <sup>3</sup>	1050
Specific Gravity		ASTM D792	-	1.05
<b>Mechanical property</b>				
Tensile strength	23°C	ISO527-1,2	MPa	56
Tensile strength		ASTM D638	MPa	53
Tensile elongation at Break		ASTM D638	%	28
Elongation at Break	23°C	ISO527-1,2	%	10
Flexural Strength	23°C	ISO178	MPa	84
Flexural Strength		ASTM D790	MPa	78
Flexural Modulus	23°C/50% RH	ISO 178	MPa	2560
Flexural Modulus		ASTM D790	MPa	2450
Rockwell Hardness	23°C	ISO2039-2	R Scale	116
Rockwell Hardness	23°C/50% RH	ASTM D785	Rスケール	116
Charpy Impact Strength (V-notched)	23°C	ISO179	kJ/m <sup>2</sup>	13
Ball Pressure Temp./0.1mm Vicat Softening Temp.			°C	95~95
Izod Impact Strength (V-notched)	23°C 12.7mm	ASTM D256	J/m	216
<b>Heat property</b>				
Heat Deflection Temp High Load	1.80MPa	ISO 75-1,2	°C	82
Heat Deflection Temp(Unannealed)High Load	6.4mm/1.82MPa	ASTM D648	°C	88
Flammability		UL94	rank/thickness mm	HB
<b>Molding property</b>				
Mold shrinkage	23°C/50% RH	Toray Method	%	0.3-0.6
Melt Flow Rate	220°C/98N	ISO 1133	g/10min	26
<b>Optical property</b>				
Gloss	an angle of incidence 60°C	Toray Method	%	98

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

**STAVIAN**<sup>®</sup>  
CHEMICAL