

TAIRILAC[®] ABS RESIN

Property	Unit	Test Method	Test Condition	General Purpose Grade
				AG15A1-H
Tensile Strength	kg/cm ² (Mpa)	ASTM D-638 (ISO 527)	23 °C	450 (43)
Flexural Strength	kg/cm ² (Mpa)	ASTM D-790 (ISO 178)	23 °C	830 (73)
Flexural Modulus	kg/cm ² (Mpa)	ASTM D-790 (ISO 178)	23 °C	26000 (2550)
Rockwell Hardness	R-scale	ASTM D-785 (ISO 2039/2)	23 °C	R-110
Izod Impact strength	kg-cm/cm (kJ/m ²)	ASTM D-256 (ISO 180)	23 °C 1/4" 23 °C 4 mm	25 (25)
Vicat Softening Point	°C	ASTM D-1525 (ISO 306)	50N	93
Heat Deflection	°C	ASTM D-648	Unannealed 1.8Mpa 1/4" · 120 °C / h	86
			Annealed 1.8Mpa 1/4" · 120 °C / h	92
Melt Flow Index	g/10 min	ASTM D-1238 (ISO 1133)	220°C×10kg(98N)	22
			200°C×5kg(49N)	2.2
Specific Gravity		ASTM D-792	23 °C/23 °C	1.05
Flammability		UL-94	File No. E162823	1.5mm HB All Color
Characteristics	Medium impact High gloss			

All tests were run under laboratory conditions, ASTM, ISO testing procedures.
The data are intended as a general guide only.

Formosa Chemicals Industries (Ningbo) Co., Ltd.

TEL: (0574) 86028116/86028186 /

FAX: (0574) 86029999-2116/2186

Address: FPG Ningbo Industrial Park Belium Ningbo, China Website:

<https://en.fcfc-plastics.com/>



台塑關係企業
FORMOSA PLASTICS GROUP

