

ER460

Injection Molding Grade

Description

- Medium Heat Resistance

Applications

- Automotive, Electric / Electronic Products

Properties	Method	Unit	ER460
Physical			
Specific Gravity , 23°C	ASTM D792		1.04
Mold Shrinkage , 23°C, 3.2mm , 23°C	ASTM D955	%	0.4 ~ 0.7
Melt Flow Rate , 220°C, 10kg	ASTM D1238	g/10min	22
Mechanical			
Tensile Strength at Yield , 23°C, 50mm/min, 3.2mm	ASTM D638	Mpa	45
Tensile Elongation at Break , 23°C, 50mm/min, 3.2mm	ASTM D638	%, (Min)	15
Tensile Modulus , 23°C, 50mm/min, 3.2mm	ASTM D638	MPa	2450
Flexural Strength , 23°C, 15mm/min, 3.2mm	ASTM D790	Mpa	80
Flexural Modulus , 23°C, 15mm/min, 3.2mm	ASTM D790	MPa	2550
Izod Impact Strength , Notched, 3.2mm, 23°C	ASTM D256	J/m	240
Izod Impact Strength , Notched, 3.2mm, -30°C	ASTM D256	J/m	100
Izod Impact Strength , Notched, 6.4mm, 23°C	ASTM D256	J/m	240
Izod Impact Strength , Notched, 6.4mm, -30°C	ASTM D256	J/m	100
Rockwell Hardness , R-Scale	ASTM D785		110
Thermal			
HDT , Edgewise, 1.82MPa, 6.4mm, Unannealed	ASTM D648	°C	92
VICAT , 50N, 50°C/h	ASTM D1525	°C	99
RTI Electrical	UL 746B	°C	60
RTI Mechanical with Impact	UL 746B	°C	60
RTI Mechanical without Impact	UL 746B	°C	60
Flammability, 1.5mm	UL 94		HB
Flammability, 3.0mm	UL 94		HB

Note

Typical values can be used only for the purpose of selecting material, and there can be variation within normal tolerances for various colors. Values given should not be interpreted as specification and not be used for designing part or tool. All properties, except melt flow rate are measured by injection molded specimens after 48 hours storage at 23°C, 50% relative humidity.

Updated Date : 8-Sep-17 Issued Date : 7-Mar-18

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.

ER460

Injection Molding Grade

Description

- Medium Heat Resistance

Applications

- Automotive, Electric / Electronic Products

Processing Guide (Injection Molding)

Processing Parameters	Unit	Value
Drying Temperature	°C	70 ~ 80
Drying Time	hrs	2 ~ 4
Maximum Moisture Content	%	0.05 ~ 0.05
Melt Temperature	°C	210 ~ 240
Cylinder Temperature , Rear	°C	180 ~ 200
Cylinder Temperature, Middle	°C	190 ~ 210
Cylinder Temperature , Front	°C	200 ~ 220
Nozzle Temperature	°C	200 ~ 230
Mold Temperature	°C	40 ~ 70
Back Pressure, Hydraulic Type	kg/cm ²	5 ~ 15

Note

Back Pressure & Measuring Speed are only mentioned as general guidelines. These may not apply or need adjustment in specific situations such as low shot sizes, thin wall molding and gas-assist molding.

STAVIAN[®]
CHEMICAL

Updated Date : 8-Sep-17 Issued Date : 7-Mar-18

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. LG Chem makes no warranty or guarantee, expressed or implied, (i) that the result described herein will be obtained under end - use conditions, or (ii) as to the effectiveness or safety of any design incorporating LG Chem materials, products, recommendations or advice. Further, any information contained herein shall not be construed as a part of legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bear full responsibility for making its own determination as to the suitability of LG Chem's materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating LG Chem material or products will be safe and suitable for use under end - use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.