

January, 2013

KOPELEN J-330

PP BLOCK COPOLYMER

General Information

Description

J-330 is impact block copolymer with ethylene content as co-monomer.

This grade is designed to be processed in conventional Injection molding equipment.

J-330 shows good impact resistance at low temperature and has also high strength.

It has broad range of property, and is used from industrial supplies to automotive compound base resin.

Applications

- General supplies & Industrial supplies
- Automotive compound base resin

| | Physical Propert | ies ¹ | | | |
|--|------------------|------------------|---------------------|-------|-----|
| Physical | Test Method | | Nominal Values | | |
| Melt Flow Index | ASTM D1238 | 4.0 | g/10min | | |
| Density | ASTM D792 | 0.90 | g/cm ³ | R | |
| Mechanical | | | | | |
| Tensile Stress (Yield) | ASTM D638 | 280 | kgf/cm ² | 26 | MPa |
| Tensile Strain (Break) | ASTM D638 | >100 | % | >100 | % |
| Flexural Modulus | ASTM D790 | 13,000 | kgf/cm ² | 1,270 | MPa |
| Impact | | | | | |
| Notched Izod Impact Strength (23℃) | ASTM D256 | 9.0 | kgf·cm/cm | 88 | J/m |
| Notched Izod Impact Strength (-10℃) | ASTM D256 | 3.0 | kgf-cm/cm | 29 | J/m |
| Thermal | | | | | |
| Heat Deflection Temperature (4.6kgf/cm²) | ASTM D648 | 105 | °C | | |
| Additional Properties | | | | | |
| Flammability | UL94 | НВ | | | |

| NOTE | ISO 9001, 14001, /TS 16949 |
|------|----------------------------|
| | |

¹ Physical Properties : these are not to be construed as specifications



January, 2013

KOPELEN J-330

PP BLOCK COPOLYMER

General Information

Description

J-330 is impact block copolymer with ethylene content as co-monomer.

This grade is designed to be processed in conventional Injection molding equipment.

J-330 shows good impact resistance at low temperature and has also high strength.

It has broad range of property, and is used from industrial supplies to automotive compound base resin.

Applications

- General supplies & Industrial supplies
- Automotive compound base resin

| | Physical Properties ¹ | | | | |
|--|----------------------------------|----------------|---------------------|-------|-----|
| Physical | Test Method | Nominal Values | | | |
| Melt Flow Index | ISO 1133 | 4.0 | g/10min | | |
| Density | ISO 1183 | 0.90 | g/cm ³ | R | |
| Mechanical | | | | V | |
| Tensile Stress (Yield) | ISO 527-1 | 270 | kgf/cm ² | 26 | MPa |
| Tensile Strain (Break) | ISO 527-1 | >100 | % | >100 | % |
| Flexural Modulus | ISO 178 | 11,000 | kgf/cm ² | 1,080 | MPa |
| Impact | | | | | |
| Notched Izod Impact Strength (23℃) | ISO 180 | 8 | kgf·cm/cm | 78 | J/m |
| Notched Izod Impact Strength (-10℃) | ISO 180 | 2.5 | kgf·cm/cm | 25 | J/m |
| Thermal | | | | | |
| Heat Deflection Temperature (4.6kgf/cm²) | ISO 75-1 | 85 | C | | |
| Additional Properties | | | | | |
| Flammability | UL94 | НВ | | | |

| NOTE | ISO 9001, 14001, /TS 16949 |
|------|----------------------------|
| NOTE | ISO 9001, 14001, /TS 16949 |

¹ Physical Properties : these are not to be construed as specifications