

SH 113

Technical Data Sheet

ABS Resin

Sinkral® SH 113 is an ABS with excellent thermal properties and good mechanical characteristics.

Sinkral® SH 113 has high processing stability which results in a very good workability.
It has a very low volatile organic content.

Applications

Sinkral® SH 113 is used in sectors such as:

- automotive
- transportation.

Typical processing data

Extrusion:

- we suggest drying for 4h at 80°C
- melt temperature 180 - 220°C

Injection moulding:

- dry for 4h at 80°C
- melt temperature 240°C
- mould temperature 70°C

Certification

✓ FMVSS 302

Storage

- ⚠ Store away from atmospheric agents and direct sunlight, away from sources of heat and light.
- 🕒 The product, if stored correctly, keeps its characteristics for at least fifteen months.

General information

Sinkral® SH 113 is available in different versions:

- natural color
- black version (SH 113 16177).

For further information, please contact Versalis directly writing to info.styrenics@versalis.eni.com.

SH 113

ABS Resin

Technical Data Sheet

Property	Test Conditions	Test method	Units	Values
General				
Water absorption	24h - 23°C	ISO 62	%	0,3
Density	-	ISO 1183	g/cm ³	1,05
Rheological				
Melt flow rate	220°C - 10kg	ISO 1133	g/10'	4,5
Mechanical				
Strain at yield	50 mm / min	ISO 527	%	2,5
Tensile stress at yield	50 mm/min	ISO 527	MPa	46
Tensile modulus	1 mm/min	ISO 527	MPa	2350
Charpy impact strength, notched	+23°C	ISO 179/1eA	kJ/m ²	13
Izod impact strength, notched	+23°C - 4mm	ISO 180/1A	kJ/m ²	14
Thermal				
Coefficient of linear thermal expansion	-	ISO 11359-2	10 ⁻⁵ /°C	9
Thermal conductivity	-	ASTM C 177	W/(K.m)	0,17
Moulding shrinkage	-	ISO 294/4	%	0,4 ÷ 0,6
Deflection temperature under load (annealed)	1,82 MPa - 120°C/h	ISO 75 A	°C	102
Deflection temperature under load (annealed)	0,45 MPa - 120°C/h	ISO 75 B	°C	109
Vicat softening temperature	10 N - 50°C/h	ISO 306/A	°C	120
Vicat softening temperature	50 N - 50°C/h	ISO 306/B	°C	113
Flammability				
Flame behaviour	1,5 mm	UL 94	cl.	HB
Glow wire test (GWT)	3 mm	IEC 60695-2-10	°C	650
Electrical				
Dielectric constant (relative permittivity)	1000 Hz secco/dry	IEC 60250	-	3,1
Dissipation factor	1000 Hz secco/dry	IEC 60250	-	15·10E-3
Surface resistivity	secco / dry	IEC 60093	ohm	10E14
Volume resistivity	secco / dry	IEC 60093	ohm·cm	10E15
Dielectric strength	secco / dry	IEC 60243	kV/mm	30

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate but no warranty or guarantee, expressed or implied, is made nor is any liability accepted.

Versalis is available to provide the guaranteed values for each product on demand.